

RUSTIKKAMEN

RUSTIK SG

Grout

Legal and technical notes: When installing our products, observe the current technical data sheets, general and regional standards, and the recommendations of the relevant national trade associations.

Applications: Cement-based grout for manufactured stone.

Properties: • Temperature resistance from -30 °C to +80 °C

Technical data					
SAP code:	**2000956432**	**2000956433**	**2000956434**	**2000956435**	**2000956436**
Packaging type					
Units per pallet	48 units/pallet (AT) 48 units/pallet (IT) 48 units/pallet (CH) 48 units/pallet (BA) 48 units/pallet (HR) 48 units/pallet (RS) 48 units/pallet (SI) 48 units/pallet (SQ)				
Quantity per pack	25 Kg/unit				
Colour	white	beige	brown	grey-brown	anthracite
Grain size	0 - 1,2 mm				
Water requirement	approx. 6,5 l/unit				
Working time	approx. 90 min				
Joint width	5 - 50 mm				
Joint depth	max. 50 mm				
Water resistance	high				
Ageing resistance	high				
Substrate temperature	> 5 - < 30 °C				

Composition:
- Cement
- Graded sand
- Additives to improve workability

Processing conditions: During application and drying, ambient and substrate temperatures must remain between +5 °C and +30 °C. Until fully dry, protect from frost, rapid drying (direct sunlight, wind) and subsequent wetting (rain). Dense scaffolding sheeting is suitable. Protect façades and façade sections exposed to weather, such as areas without canopies or eaves, with appropriate measures to prevent moisture ingress during grouting.

Substrate preparation: Joints must be dry, dust-free and cleared of adhesive and mortar residues.

Material preparation: Mix the grout in a clean container with the specified amount of water, using a mixer until smooth, homogeneous and free of lumps.

Notes: Natural raw materials may cause colour variations. To avoid façade colour differences, always use material made on the same day. The colour brilliance of cement grouts depends on substrate moisture, ambient temperature and site installation conditions. Different moisture levels and application methods may cause differences in joint colour. Given these varying conditions, we as manufacturer do not guarantee colour brilliance or workmanship. Do not grout in direct sunlight.

Rustik kamen d.o.o.
Registered office: Ulica Ljudevita Posavskog 34, HR - 10 000 Zagreb / Office and production: Oreškovićeva 1a, HR - 10 010 Zagreb
OIB: 45393613024, tel: +385 (0)1 345 00 54, fax: +385 (0)1 345 00 95, e-mail: info@rustik-kamen.hr, www.rustik-kamen.hr



RUSTIKKAMEN

RUSTIK SG

Grout

Warnings:	See each product's safety data sheet for detailed instructions. Always read the safety data sheets before use.
Storage:	Store dry on wooden pallets. Shelf life at least 12 months to Directive 1907/2006/EU at +20 °C and 65 % RH.
Declaration:	
General notes:	This data sheet replaces and invalidates all previous editions. Its information reflects our current technical knowledge and experience. Although carefully prepared, the information does not guarantee accuracy or completeness and does not constitute responsibility for users' future decisions. It creates no legal or other secondary obligation on any grounds. Users must personally check the product's suitability for their intended use. Our products and raw materials undergo continuous checks to ensure consistently high quality. Our technical sales advisers are available for questions on application, installation and presentation of our products. See each product's safety data sheet for detailed instructions and always read it before use.